


Summary of Laboratory Testing

Prime Coat

Test Procedure: TxDOT SPECIAL PROVISION 300

Specialty Prime - Asphalt, Oils, and Emulsions – Sand Penetration Test

6 March 2014



MC-30

Penetration values measured for different prime coats

	MC-30
Penetration (mm)	8

CSS-1H

Penetration values measured for different prime coats

	CSS-1H
Penetration (mm)	1

SS-1H

Penetration values measured for different prime coats

	SS-1H
Penetration (mm)	1

AEP

Penetration values measured for different prime coats

	AEP
Penetration (mm)	5

TP

Penetration values measured for different prime coats

	TP
Penetration (mm)	8

Researcher

Drit Sokoli, Civil Engineer

University of Texas at Austin

drit@utexas.edu

